



NOTES

1. OPERATION WAVELENGTH: 350 nm–1100 nm
2. OPTICAL DENSITY(OD):  $0.2 \pm 0.02 @ 635 \text{ nm}$ ;  
 $0.2 \pm 0.1 @ 350 \text{ nm} - 1100 \text{ nm}$
3. CLEAR APERTURE:  $>90\% \text{ CA}$
4. DIAMETER TOLERANCE:  $+0.00 / -0.25 \text{ mm}$
5. THICKNESS TOLERANCE:  $\pm 0.3 \text{ mm}$
6. COATING(S1): NiCrFe
7. SURFACE QUALITY(S1, S2): 40/20(S/D)
8. SURFACE FLATNESS(S1) :  $\lambda / 2 @ 632.8 \text{ nm}$
9. PARALLELISM(S1, S2) :  $< 30 \text{ arcsec}$
10. CHAMFER:  $< 0.2 \text{ mm}, 45^\circ$

DRAWING PROJECTION			<b>LBTEK</b>			
	NAME	DATE				
DRAWN	LZHOU	JUL./25th/24	REFLECTIVE ND FILTER $\phi 25.4 \text{ mm}, \text{OD}=0.2, \text{NiCrFe}, 350 \text{ nm} - 1100 \text{ nm}$			
APPROVAL	WCHENG	JUL./25th/24	MATERIAL	WEIGHT	SCALE	REV
FOR INFORMATION ONLY NOT FOR MANUFACTURING PURPOSES			N-BK7	2.46 g	2:1	A