



NOTES

1. OPERATION WAVELENGTH: 2-16 μm
2. OPTICAL DENSITY(OD): $OD_{\text{abs}}=0.3 \pm 5\% @ 5 \mu\text{m}$
 $OD_{\text{avg}}=0.3 \pm 5\% @ 2-16 \mu\text{m}$
3. CLEAR APERTURE: >90%CA
4. COATING(S1): Ni
5. SURFACE QUALITY(S1, S2): 60/40(S/D)
6. SURFACE FLATNESS(S1): $PV < \lambda @ 632.8 \text{ nm}$
7. PARALLELISM(S1, S2): <5 arcmin

DRAWING PROJECTION			LBTEK			
	NAME	DATE				
DRAWN	LTAN	JAN./4th/25	REFLECTIVE ND FILTER $\varnothing 25.4 \text{ mm}, OD=0.3, \text{Ni}; 2 \mu\text{m}-16 \mu\text{m}$			
APPROVAL	WCHENG	JAN./4th/24	MATERIAL	WEIGHT	SCALE	REV
FOR INFORMATION ONLY NOT FOR MANUFACTURING PURPOSES			ZnSe	2.75 g	2:1	A