



NOTES

1. OPERATION WAVELENGTH: 350 nm–1100 nm
2. OPTICAL DENSITY(OD): $4.0 \pm 0.2 @ 635 \text{ nm}$;
 $4.0 \pm 0.6 @ 350 \text{ nm} - 1100 \text{ nm}$
3. CLEAR APERTURE: $>90\% \text{ CA}$
4. DIAMETER TOLERANCE: $+0.00 / -0.25 \text{ mm}$
5. THICKNESS TOLERANCE: $\pm 0.3 \text{ mm}$
6. COATING(S1): NiCrFe
7. SURFACE QUALITY(S1, S2): 40/20(S/D)
8. SURFACE FLATNESS(S1) : $\lambda / 2 @ 632.8 \text{ nm}$
9. PARALLELISM(S1, S2): $< 30 \text{ arcsec}$
10. CHAMFER: $< 0.2 \text{ mm}, 45^\circ$

DRAWING PROJECTION			LBTEK			
	NAME	DATE				
DRAWN	LZHOU	JUL./25th/24	REFLECTIVE ND FILTER $\Phi 25.4 \text{ mm}, \text{OD}=4.0, \text{NiCrFe}, 350 \text{ nm}-1100 \text{ nm}$			
APPROVAL	WCHENG	JUL./25th/24	MATERIAL	WEIGHT	SCALE	REV
FOR INFORMATION ONLY NOT FOR MANUFACTURING PURPOSES			N-BK7	2.46 g	2:1	A